

MATERIALS ENGINEERING LABORATORY  
 DATA REPORT  
**PLENCO 01501**  
 Polyester  
 compression molded

PLENCO 01501 is a general purpose, mineral filled granular polyester molding compound, offering excellent arc and track resistance properties, low post shrinkage, and improved mechanical strength values. UL recognized under component file E40654. 01501 is available in gray, blue, or tan color.

PROPERTY	metric	english	ASTM Test Method
Form	briquette		
Apparent Density	0.68 g/cm <sup>3</sup>	42.3 lb/ft <sup>3</sup>	D1895
Specific Gravity	1.89		D792
Mold Shrinkage	0.0031 m/m	0.0031 in/in	D6289
Post Shrinkage 72hr 120°C	0.04 %		D6289
Izod Impact Notched	24.8 J/m	0.46 ft-lb/in	D256
Charpy Impact Notched	26.5 J/m	0.50 ft-lb/in	D256
Drop Ball Impact	137 J/m	2.6 ft-lb/in	Plenco
Tensile Strength	43 MPa	6,257 psi	D638
Tensile Modulus	12,024 MPa	1,744,000 psi	D638
Tensile Elongation	0.6 %		D638
Flexural Strength	90.5 MPa	13,127 psi	D790
Flexural Modulus	10,754 MPa	1,560,000 psi	D790
Compressive Strength	153 MPa	22,131 psi	D695
Heat Resistance	167 °C	333 °F	D794
Deflection Temperature 1.82MPa	200 °C	392 °F	D648
Water Absorption	0.30 %		D570
Rockwell Hardness	70 E scale		D785
Dielectric Strength short time	12.6 kV/mm	319 V/mil	D149
Dielectric Strength Step	10.3 kV/mm	262 V/mil	D149
Dissipation Factor, 1MHz	0.028		D150
Permittivity, 1MHz	5.3		D150
Volume Resistivity	3.2E+14 ohm-cm	1.3E+14 ohm-in	D257
ASTM Arc Resistance	190 sec		D495
Comparative Tracking Index	600 V		D3638
UL Flammability	HB @1.50mm		UL 94
Oxygen Index	24.0 %		D2863
Thermal Expansion	/°C	/°F	E831
Thermal Conductivity 100°C	0.70 W/m/°C	0.40 Btu/hr/ft/°F	E1461

Store in cool dry place.

*The Typical Values listed are results obtained from the testing of standard specimens using the stated test procedures, with said specimens molded under controlled laboratory conditions from representative samplings of the product. Although Plastics Engineering Company at all times reserves the right to make changes in the materials, suppliers and processing, the values listed as typical are those to be expected at the time of our manufacture. The final determination of the accuracy or completeness of any information, the suitability of the product for the use contemplated, the manner of its use, and the matter of any infringement of patents in use, are all the sole responsibility of the user. PLASTICS ENGINEERING COMPANY MAKES NO WARRANTY, EXPRESS OR IMPLIED, WITH RESPECT TO THIS PRODUCT, INCLUDING NO WARRANTY OF THE MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. Plastics Engineering Company reserves at all times the right to discontinue the production of any or all of its products. This is an uncontrolled copy and not subject to updates.*