

MATERIALS ENGINEERING LABORATORY
DATA REPORT
PLENCO 01501
 Polyester
 injection molded

PLENCO 01501 is a general purpose, mineral filled granular polyester molding compound, offering excellent arc and track resistance properties, low post shrinkage, and improved mechanical strength values. UL recognized under component file E40654. 01501 is available in gray, blue, or tan color.

PROPERTY	metric	english	ASTM Test Method
Form	pellet		
Apparent Density	0.82 g/cm ³	51.4 lb/ft ³	D1895
Specific Gravity	1.87		D792
Mold Shrinkage	0.0091 m/m	0.0091 in/in	D6289
Post Shrinkage 72hr 120°C	0.04 %		D6289
Izod Impact Notched	19.8 J/m	0.37 ft-lb/in	D256
Charpy Impact Notched	21.8 J/m	0.41 ft-lb/in	D256
Drop Ball Impact	133 J/m	2.5 ft-lb/in	Plenco
Tensile Strength	47 MPa	6,874 psi	D638
Tensile Modulus	10,282 MPa	1,491,000 psi	D638
Tensile Elongation	0.6 %		D638
Flexural Strength	82.9 MPa	12,017 psi	D790
Flexural Modulus	9,734 MPa	1,412,000 psi	D790
Compressive Strength	150 MPa	21,738 psi	D695
Heat Resistance	170 °C	338 °F	D794
Deflection Temperature 1.82MPa	182 °C	360 °F	D648
Water Absorption	0.24 %		D570
Rockwell Hardness	65 E scale		D785
Dielectric Strength short time	12.4 kV/mm	315 V/mil	D149
Dielectric Strength Step	10.5 kV/mm	266 V/mil	D149
Dissipation Factor, 1MHz	0.027		D150
Permittivity, 1MHz	4.9		D150
Volume Resistivity	6.6E+15 ohm-cm	2.6E+15 ohm-in	D257
ASTM Arc Resistance	187 sec		D495
Comparative Tracking Index	600 V		D3638
UL Flammability	HB @1.50mm		UL 94
Oxygen Index	24.0 %		D2863
Thermal Expansion	4.6E-05 /°C	2.5E-05 /°F	E831
Thermal Conductivity 100°C	W/m/°C	Btu/hr/ft/°F	E1461

Store in cool dry place.

The Typical Values listed are results obtained from the testing of standard specimens using the stated test procedures, with said specimens molded under controlled laboratory conditions from representative samplings of the product. Although Plastics Engineering Company at all times reserves the right to make changes in the materials, suppliers and processing, the values listed as typical are those to be expected at the time of our manufacture. The final determination of the accuracy or completeness of any information, the suitability of the product for the use contemplated, the manner of its use, and the matter of any infringement of patents in use, are all the sole responsibility of the user. PLASTICS ENGINEERING COMPANY MAKES NO WARRANTY, EXPRESS OR IMPLIED, WITH RESPECT TO THIS PRODUCT, INCLUDING NO WARRANTY OF THE MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. Plastics Engineering Company reserves at all times the right to discontinue the production of any or all of its products. This is an uncontrolled copy and not subject to updates.