

MATERIALS ENGINEERING LABORATORY
DATA REPORT
Plenco 05350
Two-Stage Phenolic
injection molded

Plenco 05350 is a mineral and graphite filled phenolic molding compound. Customers have found this material useful for seal applications. Plenco 05350 offers excellent dimensional stability, lubricity, and low abrasion properties. 05350 is available in gray. 05350 is not recommended for electrical insulating applications.

PROPERTY	metric	english	ASTM Test Method
Form	Granular		
Apparent Density	0.93 g/cm ³	58.2 lb/ft ³	D1895
Specific Gravity	1.74		D792
Mold Shrinkage*	0.0043 m/m	0.0043 in/in	D6289
Post Shrinkage 72hr 120°C	0.09 %		D6289
Izod Impact Notched	16.0 J/m	0.30 ft-lb/in	D256
Charpy Impact Notched	14.5 J/m	0.27 ft-lb/in	D256
Drop Ball Impact	38 J/m	0.7 ft-lb/in	Plenco
Tensile Strength	43 MPa	6,167 psi	D638
Tensile Modulus	15,745 MPa	2,284,000 psi	D638
Tensile Elongation	0.3 %		D638
Flexural Strength	73.0 MPa	10,582 psi	D790
Flexural Modulus	13,003 MPa	1,886,000 psi	D790
Compressive Strength	142 MPa	20,573 psi	D695
Heat Resistance	257 °C	494 °F	D794
Deflection Temperature 1.82MPa	180 °C	356 °F	D648
Water Absorption	0.05 %		D570
Rockwell Hardness	110 M scale		D785
Dielectric Strength short time	kV/mm	V/mil	D149
Dissipation Factor, 1MHz			D150
Permittivity, 1MHz			D150
Volume Resistivity	ohm-cm	ohm-in	D257
ASTM Arc Resistance	sec		D495
Comparative Tracking Index	V		D3638
UL Flammability			UL 94
Oxygen Index	41.2 %		D2863
Coefficient of Thermal Expansion	3.4E-05 /°C	1.9E-05 /°F	E831
Thermal Conductivity 100°C	1.79 W/m°C	1.04 Btu/hr/ft/°F	E1461

Store in cool dry place.

The Typical Values listed are results obtained from the testing of standard specimens using the stated test procedures, with said specimens molded under controlled laboratory conditions from representative samplings of the product. Although Plastics Engineering Company at all times reserves the right to make changes in the materials, suppliers and processing, the values listed as typical are those to be expected at the time of our manufacture. The final determination of the accuracy or completeness of any information, the suitability of the product for the use contemplated, the manner of its use, and the matter of any infringement of patents in use, are all the sole responsibility of the user. PLASTICS ENGINEERING COMPANY MAKES NO WARRANTY, EXPRESS OR IMPLIED, WITH RESPECT TO THIS PRODUCT, INCLUDING NO WARRANTY OF THE MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. Plastics Engineering Company reserves at all times the right to discontinue the production of any or all of its products. This is an uncontrolled copy and not subject to updates.

*Mold Shrinkage obtained under controlled laboratory conditions with relatively simple mold geometry and should be used for comparison purposes only and not for actual tool design.