

MATERIALS ENGINEERING LABORATORY

 DATA REPORT

Plenco 07500

 Two-Stage Phenolic

 compression molded

Plenco 07500 is an organic reinforced phenolic molding compound, offering improved mechanical strength and excellent cosmetic characteristics. UL recognized under component file E40654. 07500 is available in black, brown, or red color. 07500 was qualified under military specification MIL-M-14 (superseded by ASTM D-5948) TYPE CFG and batches can, if requested and paid for, be tested for certification to the standard.

PROPERTY	metric	english	ASTM Test Method
Form	Granular		
Apparent Density	0.52 g/cm ³	32.3 lb/ft ³	D1895
Specific Gravity	1.38		D792
Mold Shrinkage*	0.0038 m/m	0.0038 in/in	D6289
Post Shrinkage 72hr 120°C	0.16 %		D6289
Izod Impact Notched	23.3 J/m	0.44 ft-lb/in	D256
Charpy Impact Notched	24.3 J/m	0.46 ft-lb/in	D256
Drop Ball Impact	171 J/m	3.2 ft-lb/in	Plenco
Tensile Strength	54 MPa	7,878 psi	D638
Tensile Modulus	8,877 MPa	1,288,000 psi	D638
Tensile Elongation	0.7 %		D638
Flexural Strength	98.1 MPa	14,221 psi	D790
Flexural Modulus	8,739 MPa	1,267,000 psi	D790
Compressive Strength	215 MPa	31,115 psi	D695
Heat Resistance	194 °C	382 °F	D794
Deflection Temperature 1.82MPa	176 °C	349 °F	D648
Water Absorption	0.50 %		D570
Rockwell Hardness	90 E scale		D785
Dielectric Strength short time	15.5 kV/mm	394 V/mil	D149
Dissipation Factor, 1MHz	0.040		D150
Permittivity, 1MHz	4.7		D150
Volume Resistivity	2.2E+12 ohm-cm	8.9E+11 ohm-in	D257
ASTM Arc Resistance	120 sec		D495
Comparative Tracking Index	171 V		D3638
UL Flammability	HB @1.5mm		UL 94
Oxygen Index	24.9 %		D2863
Coefficient of Thermal Expansion	6.5E-05 /°C	3.6E-05 /°F	E831
Thermal Conductivity 100°C	0.37 W/m/°C	0.21 Btu/hr/ft/°F	E1461

Prior to molding compression electrical specimens, material is dried 30 min @ 90C, 110C preheat.

Store in cool dry place.

The Typical Values listed are results obtained from the testing of standard specimens using the stated test procedures, with said specimens molded under controlled laboratory conditions from representative samplings of the product. Although Plastics Engineering Company at all times reserves the right to make changes in the materials, suppliers and processing, the values listed as typical are those to be expected at the time of our manufacture. The final determination of the accuracy or completeness of any information, the suitability of the product for the use contemplated, the manner of its use, and the matter of any infringement of patents in use, are all the sole responsibility of the user. PLASTICS ENGINEERING COMPANY MAKES NO WARRANTY, EXPRESS OR IMPLIED, WITH RESPECT TO THIS PRODUCT, INCLUDING NO WARRANTY OF THE MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. Plastics Engineering Company reserves at all times the right to discontinue the production of any or all of its products. This is an uncontrolled copy and not subject to updates.

*Mold Shrinkage obtained under controlled laboratory conditions with relatively simple mold geometry and should be used for comparison purposes only and not for actual tool design.